

Test Sample	Flame Spread Index (FSI)	Smoke Developed Index (SDI)
Satine Prince Edward	110	140
Naturale Nunavut	95	300
Naturale Yukon	120	175
Naturale Niagara	95	195
Expressive Collection	120	200
Generation Collection	75	350
Maisie Juglans	125	140
Maisie Antiqued	100	175
Vintage Andover and Beach	90	400
Vintage Barn	70	400
Vintage Natural *	Not Tested	Not Tested
Vintage 2 Collection * Geometry Quadri *	Not Tested	Not Tested
Vintage 2 Collection * Geometry Quadri *	Not Tested	Not Tested
Geometry Rhombus Play and Polygon	75	185
Geometry Amazed, Zig Zag, Cubed, Vertex, and Slant	Testing in Progress	Testing in Progress
Premier & Paintable Collection	Not Tested	Not Tested
Acoustical Collection	20	200
Reclaimed Collection	Testing in Progress	Testing in Progress
New Era Collection <i>*Available Class A</i>	80	100
Acoustic Fluted Eco Collection	Not Tested	Not Tested
Cork Collection	115	135

Midnight Collection <i>*Available Class A</i>	80	100
Reclaimed Collection	Testing in Progress	Testing in Progress
Tailor Made	Not Tested	Not Tested
Ceiling Tile	25	165
Ceiling Plank	25	165

**Each batch of barn wood is different (different mix of wood species and texture). For that reason, we cannot confirm the consistency of the fire performance of the finished product, therefore these colors are not tested.*

- Flame spread / Smoke developed Index is the result (or the average of the results of multiple tests), rounded to the nearest multiple of 5. Smoke developed results in excess of 200 are rounded to the nearest multiple of 50.

CLASSIFICATION	FSI	SDI
CLASS A or I	0-25	0-450
CLASS B or II	26-75	0-450
CLASS C or III	76-200	0-450